

## Technický list

### CPRINTBB510 CPRINT PVC banner blackout 510

Laminovaný blackout banner 510g/m2, 300Dx300D 18x18.

Item	Data	Test method
Fabric	High tenacity yarns 100% PES (300D)	DIN EN ISO2060
Construction	Weaving 18x18 inch	DIN6001
Total weight	510 g/sq.m	DIN53352 BS3424 method 5A
Weight of fabric	64 g/sq.m	DIN53352 BS3424 method 5B
Weight of PVC	546 g/sq.m	DIN53352 BS3424 method 5B
Tensile strength	Warp: 600 N/5cm, Weft: 500 N/5cm	DIN53354 BS3424 method 6A
Tearing strength	Warp: 110 N, Weft: 100 N	DIN53356 BS3424 method 7A
Adhesion	60 N/5cm	DIN53357 BS3425 method 9B
Suitable temperature	(-20 °C) - (+70 °C)	DIN53372 BS3424 method 10
Flame retardancy	As requested.	
Lacquering	As requested.	

*The indexes above are on average, so there will be ±5% tolerance for actual material..*

#### Vhodné pro:

- Latexové inkousty
- Eco Solventní inkousty
- Solventní inkousty
- UV inkousty