

DirectTex® Softimage Contrast®

Field of application

Blockout

Specifications

	599150 151
	100 % polyester knit fabrics PVC-free, recyclable
	ca. 160/ 252/ 260/ 320/ 420/ 505 cm ca. 63/ 99/ 102/ 126/ 165/ 199 inch other widths available on request
	B-s1, d0 DIN EN 13501-1 Class A ASTM E84-16 NFPA 701
	ca. 220 g/m ² ca. 6.5 oz/yd ²
	ca. 0.37mm ca. 370 µm
	rolls 50/ 100 m 55/ 109 yd
	blank: 7 DIN EN ISO 105-B02
	blank: 88.76 DIN 5033-1
	length: 0.9 % cross: 0.7 % DIN EN 14704-1
	cold, ultrasonic cut
	gain factor blank: 0,93 DIN 19045-4

	length: 448.7 N cross: 683.6 N DIN EN ISO 13934-1
	length: 31.4 % cross: 53.3 % DIN EN ISO 13934-1
	total footprint: 1,650 kg CO ₂ eq./m ² determination accuracy: 84%

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside	•	•	•	•
Outside				

Article shrinkage (33 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	1,2 %	185
190°C	/ %	/ %	
200°C	/ %	/ %	
210°C	/ %	/ %	

Certifications



DirectTex® Softimage Contrast®

Field of application

Blockout



Ref.-Nr.: 599150 151 | Preview print sample