

**Technický list Z3470:54 CPRINT monomer lesk, perm, čiré**

Self-adhesive vinyl with 100 mic. monomeric PVC film, high performance permanent adhesive and 140 g/sqm PCK Paper PE one side liner. Recommended for a wide range of short term promotional applications on flat surfaces.

**SUBSTRATE**

- White soft calendered PVC, made from monomeric resins.

Finish	White Glossy		White Matte	
		Value		Tolerance
Thickness (µm)	100		100	± 10%
Opacity (%)	80		80	± 10%
Gloss (60°C) (%)	≥ 65		≤ 20	
Shrinkage (%) (MD/CD)	5 / 1,9		5 / 1,9	

**ADHESIVE**

- Clear acrylic based, permanent

**Value**

Peel Adhesion 20 min steel (N/25mm) > 12

Peel Adhesion 48 h steel (N/25mm) > 17

Application temperature (°C) > 10

Service temperature (°C) -15 to 60

LINER		
· PCK Paper PE one side		
	Value	Tolerance
Thickness (µm)	140	± 10µm
Weight (g/sqm)	140	± 10%

**DURABILITY**

- Durability: up to 2 years (unprocessed and when applied under vertical exposure - normal Central
- European climate)
- Shelf Life: 24 months from the date of manufacture, applicable only to material that has not been
- processed, and stored according to the following conditions:
- This material must be stored at a temperature of 20° C ± 5 ° C and 50% ± 5% relative humidity, without major climate deviations.
- The storage area must be dry and clean.
- Keep the material in the original package when not in use, in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.
- The product must be stored vertically, so that its quality is not compromised.

## PRINTING METHODS

- Specially developed for solvent, eco-solvent, latex and UV large format printing.
- Since the migration of the plasticizer affects the quality of the latex print, Supplier only guarantees it for 6 months. After that date the material must be used in solvent, eco-solvent and UV printing.
- This product must be protected with the recommended lamination in order to provide the necessary strength.
- For the best possible print quality, please make sure you are using the correct print profiles.
- An excessive quantity of ink in the product will result in changes in its characteristics, in inappropriate
- drying, lamination detachment and / or poor product performance.
- Inadequate drying can result in curls, wrinkles and adhesion failures, which is reflected in the result of the material's performance. A minimum drying period of 48 hours is recommended before any further processing. Drying should be done with the product unrolled.

## APPLICATIONS

- Application surface: flat
- Substrate not recommended for floor graphics (areas with car traffic); flexible or low energy substrates; non-flat surfaces; carton walls painted or unpainted; plaster walls; wallpaper; unclean or rough surfaces; surfaces with degraded paint.
- Do not expose to combustible vapors or spills.
- Surfaces on which the material will be applied must be carefully cleaned and free of dust, grease or any
- other contamination that may affect the material adhesion.
- Non-vertical application results in a significant reduction in durability, as well as climate and angles of sun exposure. It is recommended that the film remains at least 24 hours at the temperature of the workplace before it is used.
- There may be other factors not described here that may influence the performance in the use.

## IMPORTANT REMARKS

- Supplier is not responsible for the ease or speed of removal of the applied material. It is necessary to have into account the appropriate air and substrate temperatures.
- The user must determine the material's compatibility with the intended specific application, before using it.
- We recommend that, to carry out a job, the same batch of product is used.
- The data provided in this information is based on our knowledge and experience. It is intended to be a
- source of information and is not a guarantee. It can be subject to change without previous notice.
- Supplier is not responsible for misuse or improper storage, never being responsible for loss or damage to third parties.