

UFABRIK

Universal Blackback Textile

Substrate		DIN 60001,ASTM D7641	100% Polyester	
Weave			Warp-knitted 2 bar	
Yarn		DIN EN 2060,ASTM D1907	55D*75D	
Weight approx.		ISO536	260 gsm, 7.7oz/yd	
Shrinkage		200°C/45s	5.05m:≤4%, 3.2m:≤3%	
Opacity		ISO2471	>99%	
Elasticity		Warp:(3±2)% Weft:(2±1)%	Length*Width=200*50mm,Speed=100mm/min,Tension=20N	
Fire retardancy		DIN 4102-1 B1,NFPA 701 ,EN13501-1		
Recommend Fixation Temperature			190-200°C,45s	
Yellowing Temperature		SUPRKC REX-C400,30s	≥ 210°C	
Application			indoor	
Width			260, 320, 505cm / 102, 126, 199 inches	
Roll length			50, 100 m / 55, 109yd	
Type of ink		  		
Environmental elements				
	No PVC	Low-VOCs Emission	No Heavy Metal	DOP Free

Advantages

- 100% Recyclable
- Soft touch and feel
- Blockout
- Crease Resistant
- REACH compliant

Applications

- Exhibition graphics
- Blackout
- Display system
- Tension Frames
- Wall Hangings

